



Accu Tech Plastics, Inc.
1353 International Drive
Eau Claire, WI 54701 USA

Clear Polystyrene Data Sheet (PSCL)

The following table outlines the typical values for Clear Polystyrene (PSCL) product(s) produced at Accu Tech Plastics, Inc.

Property		Typical Value	Unit	Test Method
Physical:	Specific Gravity	1.02	g/cm ³	ISO 1183
	Melt Flow Rate	2.4	g/10min	ISO 1133
Tensile:	Tensile Strength @ Yield	23	MPa	ISO 527
	Tensile Elongation @ Yield	1.6	%	ISO 527
Flexural:	Flexural Strength	41	MPa	ISO 178
	Flexural Modulus	1765	MPa	ISO 178
Impact:	Notched Izod	2.67	J/m	ISO 840
Thermal:	Heat Distortion	70.5	°C	ISO 75

These values are typical in nature and are not intended for specification purposes.

Storage Life: At least one year when stored at less than 37° C (100° F), and sealed in the original packaging.

See Accu Tech Plastics, Inc. Terms & Conditions.